



PRODUCT SPECIFICATION

8" TS80 Nanofiltration Element Series

Lenntech bv
 Rotterdamseweg 402m
 2629HH Delft
info@lenntech.com
www.lenntech.com
 Tel. +31-15-261.09.00
 Fax. +31-15-261.62.89

Model	Permeate flow GPD (m3/day)*	Average Salt Rejection (%)	Minimum Salt Rejection (%)
8040-TS80-TSA	9,000 (34.0)	99.00	97.00

Performance is based on the following test conditions: 2,000.0 ppm MgSO₄, 110.0 psi, 25°C, 15% recovery, pH 8.0, 30 minutes operation.

OPERATIONAL AND DESIGN DATA

Membrane Type.....	ANM Aromatic Polyamide Advanced Nanofiltration Membrane
Configuration.....	Spiral Wound, Fiberglass Outer Wrap
Active Membrane Area.....	365 ft ² (33.5 m ²)
Recommended Applied Pressure.....	40 - 200 psi (3 - 14 bar)
Maximum Applied Pressure.....	600 psi (41 bar)
Recommended Operating Temperature.....	35 - 113°F (2 - 45°C)
Feedwater pH Range.....	2 - 11 continuous
Chlorine Tolerance.....	<0.1 ppm
Maximum Feed Flow.....	80 GPM (18 m ³ /hr)
Minimum Brine Flow/Permeate Flow Ratio....	5:1
Maximum SDI (15 minutes)	5.0
Maximum Turbidity.....	1 NTU



Element Weight : 45 (20)
 Length (A) : 40.0 (1,016) Diameter (B) : 7.9 (200) Permeate Tube (C) : 1.50 (38.1)
 Units in pounds and inches, units in paranthesis in kilograms and millimetres.
 Mechanical Configuration: TriSep Style Core Tube
 Feed Spacer: 0.031" thick diamond spacer

* Permeate flow is clean water flux at standard conditions above. Not applicable for all feedwater conditions. Individual element's permeate flow may vary +/- 15%.



Engineered Membrane
SOLUTIONS