

FILMTEC Membranes

FILMTEC Fibreglassed Elements for Light Industrial Systems

Features

FILMTEC™ brackish water reverse osmosis membrane elements provide consistent, outstanding system performance in light industrial applications.

- FILMTEC BW30LE-4040 delivers highest performance at lowest pressure resulting in less energy usage and lower costs.
- FILMTEC BW30-4040 is the industry standard for reliable operation and production of the highest quality water.
- FILMTEC BW30-2540 elements are designed for systems smaller than 1 gpm (0.2 m³/h) offering a hard shell exterior for extra strength.


Elements with a hard shell exterior are recommended for systems with multiple-element housings containing three or more membranes, as they are designed to withstand higher pressure drops.

Product Specifications

Product	Part Number	Active Area ft ² (m ²)	Applied Pressure psig (bar)	Permeate Flow Rate gpd (m ³ /d)	Stabilized Salt Rejection (%)
BW30LE-4040	80604	82 (7.6)	150 (10.3)	2,300 (8.7)	99.0
BW30-4040	80783	82 (7.6)	225 (15.5)	2,400 (9.1)	99.5
BW30-2540	80766	28 (2.6)	225 (15.5)	850 (3.2)	99.5

1. Permeate flow and salt rejection based on the following test conditions: 2,000 ppm NaCl, pressure specified above, 77°F (25°C) and 15% recovery.
2. Permeate flows for individual elements may vary +/-20%.
3. For the purpose of improvement, specifications may be updated periodically.
4. BW30LE-4040 was previously named BW30HP-4040.

Figure 1



Dimensions – Inches (mm)

Product	A	B	C	D
BW30LE-4040	40.0 (1,016)	1.05 (26.7)	0.75 (19)	3.9 (99)
BW30-4040	40.0 (1,016)	1.05 (26.7)	0.75 (19)	3.9 (99)
BW30-2540	40.0 (1,016)	1.19 (30.2)	0.75 (19)	2.4 (61)

1. Refer to FilmTec Design Guidelines for multiple-element systems.
 2. BW30-2540 elements fit nominal 2.5-inch I.D. pressure vessel. BW30LE-4040 and BW30-4040 elements fit nominal 4-inch I.D. pressure vessel.
- 1 inch = 25.4 mm

Operating Limits	<ul style="list-style-type: none">• Membrane Type• Maximum Operating Temperature^a• Maximum Operating Pressure• Maximum Feed Flow Rate - 4040 elements• - 2540 elements• Maximum Pressure Drop• pH Range, Continuous Operation^a• pH Range, Short-Term Cleaning^b• Maximum Feed Silt Density Index• Free Chlorine Tolerance^c	Polyamide Thin-Film Composite 113°F (45°C) 600 psi (41 bar) 16 gpm (3.6 m ³ /h) 6 gpm (1.4 m ³ /h) 15 psig (1.0 bar) 2 – 11 1 – 12 SDI 5 <0.1 ppm
	<p>^a Maximum temperature for continuous operation above pH 10 is 95°F (35°C).</p> <p>^b Refer to Cleaning Guidelines in specification sheet 609-23010.</p> <p>^c Under certain conditions, the presence of free chlorine and other oxidizing agents will cause premature membrane failure. Since oxidation damage is not covered under warranty, FilmTec recommends removing residual free chlorine by pretreatment prior to membrane exposure. Please refer to technical bulletin 609-22010 for more information.</p>	
Important Information	<p>Proper start-up of reverse osmosis water treatment systems is essential to prepare the membranes for operating service and to prevent membrane damage due to overfeeding or hydraulic shock. Following the proper start-up sequence also helps ensure that system operating parameters conform to design specifications so that system water quality and productivity goals can be achieved.</p> <p>Before initiating system start-up procedures, membrane pretreatment, loading of the membrane elements, instrument calibration and other system checks should be completed.</p> <p>Please refer to the application information literature entitled "Start-Up Sequence" (Form No. 609-00298) for more information.</p>	
Operation Guidelines	<p>Avoid any abrupt pressure or cross-flow variations on the spiral elements during start-up, shutdown, cleaning or other sequences to prevent possible membrane damage. During start-up, a gradual change from a standstill to operating state is recommended as follows:</p> <ul style="list-style-type: none">• Feed pressure should be increased gradually over a 30-60 second time frame.• Cross-flow velocity at set operating point should be achieved gradually over 15-20 seconds.• Permeate obtained from first hour of operation should be discarded.	
General Information	<ul style="list-style-type: none">• Keep elements moist at all times after initial wetting.• If operating limits and guidelines given in this bulletin are not strictly followed, the limited warranty will be null and void.• To prevent biological growth during prolonged system shutdowns, it is recommended that membrane elements be immersed in a preservative solution.• The customer is fully responsible for the effects of incompatible chemicals and lubricants on elements.• Maximum pressure drop across an entire pressure vessel (housing) is 50 psi (3.4 bar).• Avoid static permeate-side backpressure at all times.	