

PRODUCT DATA SHEET

AMBERLITE™ IRA67

Industrial Grade Weak Base Anion Exchanger

AMBERLITE IRA67 resin is a weak base anion exchange resin with a gel type acrylic matrix. It has a high capacity, excellent physical stability, fast kinetics, outstanding resistance to organic fouling and basicity higher than that of polystyrenic weak base resins.

The flexible acrylic structure of AMBERLITE IRA67 resin allows for effective adsorption and desorption of naturally occurring organic molecules, such as humic and fulvic acids, that are present in many water supplies.

PROPERTIES

Physical form _____	Translucent white spherical beads
Matrix _____	Crosslinked acrylic gel structure
Functional group _____	Tertiary amine
Ionic form as shipped _____	Free Base (FB)
Total exchange capacity ^[1] _____	≥ 1.60 eq/L (FB form)
Moisture holding capacity ^[1] _____	56 to 64 % (FB form)
Shipping weight _____	700 g/L
Particle size _____	
Uniformity coefficient ^[1] _____	≤ 1.80
Harmonic mean size ^[1] _____	0.500 – 0.750 mm
< 0.300 mm ^[1] _____	3.0 % max
Reversible swelling _____	FB → Cl ⁻ ≤ 30 %

^[1] Contractual value

Test methods are available on request.

SUGGESTED OPERATING CONDITIONS

Maximum operating temperature _____	60 °C
Minimum bed depth _____	700 mm
Service flow rate _____	5 to 40 BV*/h
Regeneration _____	
Regenerant _____	NaOH
Level _____	130 % of ionic load
Concentration _____	2 to 4 %
Minimum contact time _____	30 minutes
Slow rinse _____	2 BV at regeneration flow rate
Fast rinse _____	8 to 16 BV at 10 BV/h

* 1 BV (Bed Volume) = 1 m³ solution per m³ resin

PERFORMANCE

Operating capacity

The operating exchange capacity of AMBERLITE IRA67 resin depends on a number of factors:

- composition of water (particularly CO₂ and SO₄ content),
- specific flow rate,
- ionic load.

AMBERLITE IRA67 resin offers an operating capacity 15 to 30 % higher than that of polystyrenic weak base resins.

The engineering data sheet EDS 0255 A provides information to calculate the operating capacity of AMBERLITE IRA67 resin.

Regeneration

Optimum regeneration conditions correspond to a quantity of caustic soda equivalent to 120 to 140 % of the operating capacity. It is not recommended to use higher regeneration ratios, as the excess caustic soda might lead to an increase of the rinse water volume required. The latter can be minimised by recycling the rinse effluent through the upstream cation exchange resin.

Organic matter

The aliphatic structure of AMBERLITE IRA67 resin gives it slightly less affinity for organic acids found in surface waters than polystyrene weak base resins. This weaker affinity combined with the flexible acrylic polymer structure allows for more complete elution of the organics from the resin. Therefore, AMBERLITE IRA67 resin offers a large reversible capacity for the removal of organic matter.

HYDRAULIC CHARACTERISTICS

AMBERLITE IRA67 resin gives a pressure drop of about 18 kPa/m bed depth per 10 m/h at 15 °C. A backwash flow rate of 4 m/h gives a bed expansion of about 65 % at 15 °C.

LIMITS OF USES

AMBERLITE IRA67 resin is suitable for industrial water treatment. For all other specific applications such as pharmaceutical, food processing or potable water applications, it is recommended that all potential users seek advice from Rohm and Haas in order to determine the best resin choice and optimum operating conditions.

Lenntech bv
Rotterdamseweg 402m
2629HH Delft
info@lenntech.com
www.lenntech.com
Tel. +31-15-261.09.00
Fax. +31-15-261.62.89