



LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289

Dow
Liquid Separations

DOWEX Ion Exchange Resins

For Condensate Polishing

March 2005

DOWEX Ion Exchange Resins – For Condensate Polishing

Product Overview

DOWEX* condensate polishing grade resins are premium grade products with high exchange capacity, excellent resistance to attrition, and good resistance to thermal and oxidative degradation. DOWEX MONOSPHERE* resins are uniform particle size resins specifically designed for use in mixed beds. These resins are ideally suited to the high flow rate demands of condensate polishing applications.

Product	Resin Types	Matrix	Ionic Forms	Total Capacity eq/l, min.	Water Content %	Uniformity Coefficient	Particle Size microns			WUBS	Crush Strength g/bead		H+, min. %	Cl-, max. %
							mean	% >850	% <300		Avg., min.	% >200		
DOWEX MONOSPHERE 650C	Strong Acid Cation	Styrene DVB Gel	H ⁺	2.0	46-51	1.1	650±50	5	0.5	95	500	95	99.7	-
DOWEX MONOSPHERE 545C	Strong Acid Cation	Styrene DVB Gel	H ⁺	2.5	36-42	1.1	525±50	3	1	95	500	95	99.7	-
DOWEX MONOSPHERE 575C	Strong Acid Cation	Styrene DVB Gel	H ⁺	2.3	41-46	1.1	550±50	5	0.5	95	500	95	99.7	-
DOWEX MONOSPHERE 650 HXC	Strong Acid Cation	Styrene DVB Gel	H ⁺	2.2	39-44	1.1	650±50	5	0.2	95	500	95	99.7	-
DOWEX MONOSPHERE 750C	Strong Acid Cation	Styrene DVB Gel	H ⁺	2.0	46-51	1.15	765±25	5 ¹	0.5 ²	95	500	95 ³		-
DOWEX MONOSPHERE MP-525C	Strong Acid Cation	Styrene DVB Macroporous	H ⁺	1.6	50-54	1.1	500±50	-	1	95 ¹			-	-
DOWEX MONOSPHERE 550A	Strong Base Anion Type 1	Styrene DVB Gel	OH ⁻	1.1	55-65	1.1	590±50	5	0.5	95	350	95	-	0.5
DOWEX MONOSPHERE 700A	Strong Base Anion Type 1	Styrene DVB Gel	OH ⁻	1.1	55-65	1.1	700±580	5	0.5	95	350	95	-	0.5
DOWEX MONOSPHERE MP-725A	Strong Base Anion Type 1	Styrene DVB Macroporous	OH ⁻	0.8	65-75	1.1	690±50	5	0.5	95 ¹	-	-	-	0.5
DOWEX MONOSPHERE 600 BB	Inert	Styrene DVB Acrylate Gel	Inert	-	-	1.1	600±50	-	-	-	-	-	-	-
Product	Resin Types	Matrix	Ionic Forms	Total Capacity eq/l, min.	Water Content %	Uniformity Coefficient	Particle Size % max.			WUBS	Crush Strength g/bead		H+, min.	Cl-, max.
							>16 mesh	<40 mesh	<45 mesh		Avg., min.	% >200		
DOWEX HCR-W2	Strong Acid Cation	Styrene DVB Gel	H ⁺	1.8	48-54	-	2	1	-	95	350	95	-	-
DOWEX HGR-W2	Strong Acid Cation	Styrene DVB Gel	H ⁺	2.0	47-51	-	2	1	-	95	350	95	-	-
DOWEX SBR-C	Strong Base Anion Type 1	Styrene DVB Gel	Cl ⁻ OH ⁻	1.4 1.1	43-48 50-60	- -	2 5	- -	1 1	95 95	350 350	95 95	- -	- 1
DOWEX SBR-LC NG	Strong Base Anion Type 1	Styrene DVB Gel	OH ⁻	1.2	60 max	-	2	1	0.2	95	350	95	-	-

[†] Data represents Whole Beads, min.

¹ %>900

² %<400

³ %>300

Dow Liquid Separations Offices.
For more information call Dow Liquid Separations:

LENNTECH

info@lennotech.com Tel. +31-152-610-900
www.lennotech.com Fax. +31-152-616-289

Notice: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

