

Lewatit® MonoPlus TP 208 is a weakly acidic, macroporous cation exchange resin with chelating imino-diacetate groups for the selective removal of alkaline earth cations. The monodisperse beads are mechanically and osmotically superior stable. The optimized kinetics lead to an increased operating capacity compared to ion exchange resins with heterodisperse bead size distribution.

In comparison to **Lewatit® TP 207** and **Lewatit® MonoPlus TP 207** this resin has a modified polymer structure and also a modified substitution grade of the imino-diacetate groups to make it especially suitable for the adsorption of earth alkali ions in the presence of alkali ions.

It is especially suitable for use in:

- » final polishing of brine feed to chloralkali membrane cells (traces of alkaline earth ions are removed after their normal precipitation by carbonates in the pH-range 8-11) in the presence of iron (III) ions and in case Sr and Ba has also to be removed besides of Ca and Mg

The operating capacity of **Lewatit® MonoPlus TP 208** depends on the pH-value of the brine. At pH 10 it is approx. threefold of that achieved at pH 7. At pH 10 and calcium content of 5 ppm, an operating capacity of approx. 13 gCa/l **Lewatit® MonoPlus TP 208** (volume of resin in di-sodium-form) is obtained. At a service flow rate of 20-30 BV/h, the residual calcium concentration is well below 20 ppb. Greater security can be achieved by operating two units of equal size in series.

Lewatit® MonoPlus TP 208 has to be conditioned with caustic soda solution after every regeneration cycle/before every exhaustion cycle. After the conditioning it is in di-sodium-form and ready to use or the final polishing of chloralkali brine feed.

Aside from its major application in brine purification **Lewatit® MonoPlus TP 208** can be used for the removal or recovery of heavy metals out of process-, waste water- and potable streams. Thereby, it removes heavy metal cations from neutralized aqueous solutions in the following order:

Copper > Vanadium (VO_2^{2+}) > Uranium (UO_2^{2+}) > Lead > Nickel > Zinc > Cadmium > Iron (II) > Beryllium > Manganese > Calcium > Magnesium > Strontium > Barium > Sodium. **Lewatit® MonoPlus TP 208** does not remove heavy metals from solutions containing EDTA or NTA respectively. Only cadmium is removed from solutions containing cyanides.

The special properties of this product can only be fully utilized if the technology and process used correspond to the current state-of-the-art. Further advice in this matter can be obtained from Lanxess, Business Unit Ion Exchange Resins.

General Description

Ionic form as shipped	Na ⁺
Functional group	iminodiacetic acid
Matrix	crosslinked polystyrene
Structure	macroporous
Appearance	beige, opaque

Physical and Chemical Properties

		metric units	
Total capacity*	H-Form	min. eq/l	2.5
Uniformity Coefficient*		max.	1.1
Mean bead size*		mm	0.65 (+/- 0.05)
Bulk density	(+/- 5 %)	g/l	740
Density		approx. g/ml	1.16
Water retention		wt. %	58 - 64
Volume change	Na ⁺ --> H ⁺	max. vol. %	-30
Stability	at pH-range		0 - 14
Storability	of the product	max. years	2
Storability	temperature range	°C	-20 - 40

* Specification values subjected to continuous monitoring.

Recommended Operating Conditions*

		metric units	
Operating temperature		max. °C	80
Operating pH-range			2 - 12
Bed depth		min. mm	1000
Specific pressure drop	(15 °C)	approx. kPa*h/m²	1.0
Pressure drop		max. kPa	250
Linear velocity	operation	max. m/h	40
Linear velocity	backwash (20 °C)	approx. m/h	10
Bed expansion	(20 °C, per m/h)	approx. vol. %	5
Freeboard	backwash	vol. %	min. 80
Regenerant			HCl
Co current regeneration	level	approx. g/l	140 - 150
Co current regeneration	concentration	approx. wt. %	4 - 10
Linear velocity	regeneration	approx. m/h	5
Linear velocity	rinsing	approx. m/h	5
Conditioning			NaOH
Conditioning			Di-Na
Conditioning	level	g/l	80 - 88
Conditioning	concentration	approx. wt. %	4
Linear velocity	conditioning	approx. m/h	5
Linear velocity	rinsing	approx. m/h	5
Rinse water requirement		approx. BV	5

The recommended operating conditions refer to the use of the product under normal operating conditions. It is based on tests in pilot plants and data obtained from industrial applications. However, additional data are needed to calculate the resin volumes required for industrial scale ion exchange units. These can be found in our technical data sheets, have to be requested from Lanxess-application-specialists or have to be elaborated in laboratory- and pilot-tests.

Additional Information & Regulations

Safety precautions

Strong oxidants, e.g. nitric acid, can cause violent reactions if they come into contact with ion exchange resins.

Toxicity

The safety data sheet must be observed. It contains additional data on product description, transport, storage, handling, safety and ecology.

Disposal

In the European Community ion exchange resins have to be disposed, according to the European waste nomenclature which can be accessed on the internet-site of the European Union.

Storage

It is recommended to store ion exchange resins at temperatures above the freezing point of water under roof in dry conditions without exposure to direct sunlight. If resin should become frozen, it should not be mechanically handled and left to thaw out gradually at ambient temperature. It must be completely thawed before handling or use. No attempt should be made to accelerate the thawing process.

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



WATER TREATMENT SOLUTIONS

info@lennotech.com Tel. +31-152-610-900

www.lennotech.com Fax. +31-152-616-289

For more information or a quote, please use the